

technical data

Technical data DLS ECKLITE SC 15 triple glazing

		DLS ECKLITE SC 15– CLIMATOP ULTRA, triple glazing, U_g 0,6 W/m ² .K ** at sun angle		
		0°	30°	60°
		louvre setting		
		opened*	closed	approx. 45°
τ_A	0,70	0,04	0,07	0,14
ρ_A	0,14	0,63	0,58	0,35
τ_{D65}	0,70	0,04	0,07	0,14
ρ_{D65}	0,14	0,64	0,53	0,35
$\tau_{e,Glo}$	0,38	0,02	0,04	0,08
$\rho_{e,Glo}$	0,24	0,57	0,52	0,32
q_i	0,12	0,05	0,06	0,08
g	0,50	0,07	0,10	0,17

* acc. EN 410 / ** values acc. report TU-Berlin HK-EG11-01