



Pane 1	ORAÉ (6 mm) COOL-LITE SKN 183
Cavity 1	ARGON (90%) / AIR (10%) / 16 mm
Pane 2	ORAÉ (4 mm)

Foster + Partner - Sample 9  
Climaplus SKN 183 - 6 (16AR) 4 - all base glasses OARE`

vandaglas Eckelt GmbH  
application engineering  
Karl Seiringer  
Resthofstraße 18  
4400 Steyr  
Austria  
+43 7252 894 1116  
karl.seiringer@vandaglas.at



## LUMINOUS FACTORS

CIE015:2018

Light transmission (TL %)	75 %
Outdoor reflection (RLe %)	12 %
Indoor (RLi %)	13 %



## SOLAR FACTORS

EN410:2011

Solar factor (g)	0,40 (solar heat gain coefficient)
Shading Coefficient (SC)	0,46



## COLOR RENDERING

CIE015:2018

Transmission (Ra)	94,7
Reflection (Ra)	84,4



## CARBON FOOTPRINT

EN15804:2012+A2:2019

Global warming potential 'GWP' 24 Kg(CO2)/m²  
(A1-A3)



## ENERGY FACTORS

EN410:2011

Transmission (Te)	38 %
Reflection (Ree)	35 %
Indoor (Rei)	39 %
Absorption (AE1)	26 %
Absorption (AE2)	1 %



## THERMAL TRANSMISSION

EN673:2011

Ug	1,0 W/m².K
0° related to vertical position	



## MANUFACTURING SIZES

Nominal thickness	26,0 mm
Weight	25 kg/m²